

LINDE+LARSEN

MATERIAL SPECIFICATION

GRADE:	A.S. 22		
TYPE:	ANTI-STATIC FLEXIBLE URETHANE FOAM		
COLOUR:	PINK		
DENSITY:	20-24 KG/M ³		B.S. 4443
HARDNESS:	90-120 N		B.S. 4443
TENSILE STRENGTH:	100 Kpa		B.S. 4443
ELONGATION AT BREAK:	200 %		B.S. 4443
COMPRESSION SET (MAX)	8 %		B.S. 4443
SURFACE RESISTIVITY:	10 ¹⁰ - 10 ¹²	OHMS SQ-1	ASTM D257